

Section Properties of Structural Glued Laminated Timber

American Institute of Timber Construction

Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size				x-x Axis			y-y Axis		DF-L	HF
				A	S _x	I _x	S _y	I _y	Weight per foot	Weight per foot
b	d	Area	Section Modulus	Moment of Inertia	Section Modulus	Moment of Inertia	(based on 35 lb/ft ³)	(based on 27 lb/ft ³)		
Width	Depth								in. ²	in. ³
2	1/8	X	3	6.375	3.188	4.781	2.258	2.399	1.5	1.2
2	1/8	X	4 1/2	9.563	7.172	16.14	3.387	3.598	2.3	1.8
2	1/8	X	6	12.75	12.75	38.25	4.516	4.798	3.1	2.4
2	1/8	X	7 1/2	15.94	19.92	74.71	5.645	5.997	3.9	3.0
2	1/8	X	9	19.13	28.69	129.1	6.773	7.197	4.6	3.6
2	1/8	X	10 1/2	22.31	39.05	205.0	7.902	8.396	5.4	4.2
2	1/8	X	12	25.50	51.00	306.0	9.031	9.596	6.2	4.8
2	1/8	X	13 1/2	28.69	64.55	435.7	10.16	10.80	7.0	5.4
2	1/8	X	15	31.88	79.69	597.7	11.29	11.99	7.7	6.0
2	1/8	X	16 1/2	35.06	96.42	795.5	12.42	13.19	8.5	6.6
2	1/8	X	18	38.25	114.8	1033	13.55	14.39	9.3	7.2
2	1/8	X	19 1/2	41.44	134.7	1313	14.68	15.59	10.1	7.8
2	1/2	X	3	7.500	3.750	5.625	3.125	3.906	1.8	1.4
2	1/2	X	4 1/2	11.25	8.438	18.98	4.688	5.859	2.7	2.1
2	1/2	X	6	15.00	15.00	45.00	6.250	7.813	3.6	2.8
2	1/2	X	7 1/2	18.75	23.44	87.89	7.813	9.766	4.6	3.5
2	1/2	X	9	22.50	33.75	151.9	9.375	11.72	5.5	4.2
2	1/2	X	10 1/2	26.25	45.94	241.2	10.94	13.67	6.4	4.9
2	1/2	X	12	30.00	60.00	360.0	12.50	15.63	7.3	5.6
2	1/2	X	13 1/2	33.75	75.94	512.6	14.06	17.58	8.2	6.3
2	1/2	X	15	37.50	93.75	703.1	15.63	19.53	9.1	7.0
2	1/2	X	16 1/2	41.25	113.4	935.9	17.19	21.48	10.0	7.7
2	1/2	X	18	45.00	135.0	1215.0	18.75	23.44	10.9	8.4
2	1/2	X	19 1/2	48.75	158.4	1545	20.31	25.39	11.8	9.1
3	1/8	X	3	9.375	4.688	7.031	4.883	7.629	2.3	1.8
3	1/8	X	4 1/2	14.06	10.55	23.73	7.324	11.44	3.4	2.6
3	1/8	X	6	18.75	18.75	56.25	9.766	15.26	4.6	3.5
3	1/8	X	7 1/2	23.44	29.30	109.9	12.21	19.07	5.7	4.4
3	1/8	X	9	28.13	42.19	189.8	14.65	22.89	6.8	5.3
3	1/8	X	10 1/2	32.81	57.42	301.5	17.09	26.70	8.0	6.2
3	1/8	X	12	37.50	75.00	450.0	19.53	30.52	9.1	7.0
3	1/8	X	13 1/2	42.19	94.92	640.7	21.97	34.33	10.3	7.9
3	1/8	X	15	46.88	117.2	878.9	24.41	38.15	11.4	8.8
3	1/8	X	16 1/2	51.56	141.8	1170	26.86	41.96	12.5	9.7
3	1/8	X	18	56.25	168.8	1519	29.30	45.78	13.7	10.5
3	1/8	X	19 1/2	60.94	198.0	1931	31.74	49.59	14.8	11.4
3	1/8	X	21	65.63	229.7	2412	34.18	53.41	16.0	12.3
3	1/8	X	22 1/2	70.31	263.7	2966	36.62	57.22	17.1	13.2
3	1/8	X	24	75.00	300.0	3600	39.06	61.04	18.2	14.1
3	1/8	X	25 1/2	79.69	338.7	4318	41.50	64.85	19.4	14.9
3	1/8	X	27	84.38	379.7	5126	43.95	68.66	20.5	15.8
3	1/8	X	28 1/2	89.06	423.0	6028	46.39	72.48	21.6	16.7
3	1/8	X	30	93.75	468.8	7031	48.83	76.29	22.8	17.6
3	1/2	X	3	10.50	5.250	7.875	6.125	10.72	2.6	2.0
3	1/2	X	4 1/2	15.75	11.81	26.58	9.188	16.08	3.8	3.0
3	1/2	X	6	21.00	21.00	63.00	12.25	21.44	5.1	3.9
3	1/2	X	7 1/2	26.25	32.81	123.00	15.31	26.80	6.4	4.9

Section Properties of Structural Glued Laminated Timber
American Institute of Timber Construction
Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size				x-x Axis			y-y Axis		DF-L	HF
				A	S _x	I _x	S _y	I _y	Weight per foot	Weight per foot
b	d	Area	Section Modulus	Moment of Inertia	Section Modulus	Moment of Inertia	(based on 35 lb/ft ³)	(based on 27 lb/ft ³)		
Width	Depth								in. ²	in. ³
in.	in.									
3	1/2	X	9	31.50	47.25	212.6	18.38	32.16	7.7	5.9
3	1/2	X	10	36.75	64.31	337.6	21.44	37.52	8.9	6.9
3	1/2	X	12	42.00	84.00	504.0	24.50	42.88	10.2	7.9
3	1/2	X	13	47.25	106.3	717.6	27.56	48.23	11.5	8.9
3	1/2	X	15	52.50	131.3	984.4	30.63	53.59	12.8	9.8
3	1/2	X	16	57.75	158.8	1310	33.69	58.95	14.0	10.8
3	1/2	X	18	63.00	189.0	1701	36.75	64.31	15.3	11.8
3	1/2	X	19	68.25	221.8	2163	39.81	69.67	16.6	12.8
3	1/2	X	21	73.50	257.3	2701	42.88	75.03	17.9	13.8
3	1/2	X	22	78.75	295.3	3322	45.94	80.39	19.1	14.8
3	1/2	X	24	84.00	336.0	4032	49.00	85.75	20.4	15.8
3	1/2	X	25	89.25	379.3	4836	52.06	91.11	21.7	16.7
3	1/2	X	27	94.50	425.3	5741	55.13	96.47	23.0	17.7
3	1/2	X	28	99.75	473.8	6752	58.19	101.8	24.2	18.7
3	1/2	X	30	105.0	525.0	7875	61.25	107.2	25.5	19.7
5	1/8	X	3	15.38	7.688	11.53	13.13	33.65	3.7	2.9
5	1/8	X	4	23.06	17.30	38.92	19.70	50.48	5.6	4.3
5	1/8	X	6	30.75	30.75	92.25	26.27	67.31	7.5	5.8
5	1/8	X	7	38.44	48.05	180.2	32.83	84.13	9.3	7.2
5	1/8	X	9	46.13	69.19	311.3	39.40	101.0	11.2	8.6
5	1/8	X	10	53.81	94.17	494.4	45.96	117.8	13.1	10.1
5	1/8	X	12	61.50	123.0	738.0	52.53	134.6	14.9	11.5
5	1/8	X	13	69.19	155.7	1051	59.10	151.4	16.8	13.0
5	1/8	X	15	76.88	192.2	1441	65.66	168.3	18.7	14.4
5	1/8	X	16	84.56	232.5	1919	72.23	185.1	20.6	15.9
5	1/8	X	18	92.25	276.8	2491	78.80	201.9	22.4	17.3
5	1/8	X	19	99.94	324.8	3167	85.36	218.7	24.3	18.7
5	1/8	X	21	107.6	376.7	3955	91.93	235.6	26.2	20.2
5	1/8	X	22	115.3	432.4	4865	98.50	252.4	28.0	21.6
5	1/8	X	24	123.0	492.0	5904	105.1	269.2	29.9	23.1
5	1/8	X	25	130.7	555.4	7082	111.6	286.0	31.8	24.5
5	1/8	X	27	138.4	622.7	8406	118.2	302.9	33.6	26.0
5	1/8	X	28	146.1	693.8	9887	124.8	319.7	35.5	27.4
5	1/8	X	30	153.8	768.8	11530	131.3	336.5	37.4	28.8
5	1/8	X	31	161.4	847.5	13350	137.9	353.4	39.2	30.3
5	1/8	X	33	169.1	930.2	15350	144.5	370.2	41.1	31.7
5	1/8	X	34	176.8	1017	17540	151.0	387.0	43.0	33.2
5	1/8	X	36	184.5	1107	19930	157.6	403.8	44.8	34.6
5	1/8	X	37	192.2	1201	22520	164.2	420.7	46.7	36.0
5	1/8	X	39	199.9	1299	25330	170.7	437.5	48.6	37.5
5	1/8	X	40	207.6	1401	28370	177.3	454.3	50.5	38.9
5	1/8	X	42	215.3	1507	31640	183.9	471.1	52.3	40.4
5	1/8	X	43	222.9	1616	35150	190.4	488.0	54.2	41.8
5	1/8	X	45	230.6	1730	38920	197.0	504.8	56.0	43.2
5	1/8	X	46	238.3	1847	42940	203.6	521.6	57.9	44.7
5	1/8	X	48	246	1968	47230	210.1	538.4	59.8	46.1
5	1/2	X	3	16.5	8.25	12.38	15.13	41.59	4.0	3.1

Section Properties of Structural Glued Laminated Timber

American Institute of Timber Construction

Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size				x-x Axis			y-y Axis		DF-L	HF	
				A	S _x	I _x	S _y	I _y	Weight per foot	Weight per foot	
b	d	Area	Section Modulus	Moment of Inertia	Section Modulus	Moment of Inertia	(based on 35 lb/ft ³)	(based on 27 lb/ft ³)			
Width	Depth	in. ²	in. ³	in. ⁴	in. ³	in. ⁴	lb/ft	lb/ft			
in.	in.										
5	1/2	X	4	1/2	24.75	18.56	41.77	22.69	62.39	6.0	4.6
5	1/2	X	6		33.00	33.00	99.00	30.25	83.19	8.0	6.2
5	1/2	X	7	1/2	41.25	51.56	193.4	37.81	104.0	10.0	7.7
5	1/2	X	9		49.50	74.25	334.1	45.38	124.8	12.0	9.3
5	1/2	X	10	1/2	57.75	101.1	530.6	52.94	145.6	14.0	10.8
5	1/2	X	12		66.00	132.0	792.0	60.50	166.4	16.0	12.4
5	1/2	X	13	1/2	74.25	167.1	1128	68.06	187.2	18.0	13.9
5	1/2	X	15		82.50	206.3	1547	75.63	208.0	20.1	15.5
5	1/2	X	16	1/2	90.75	249.6	2059	83.19	228.8	22.1	17.0
5	1/2	X	18		99.00	297.0	2673	90.75	249.6	24.1	18.6
5	1/2	X	19	1/2	107.3	348.6	3398	98.31	270.4	26.1	20.1
5	1/2	X	21		115.5	404.3	4245	105.9	291.2	28.1	21.7
5	1/2	X	22	1/2	123.8	464.1	5221	113.4	312.0	30.1	23.2
5	1/2	X	24		132.0	528.0	6336	121.0	332.8	32.1	24.8
5	1/2	X	25	1/2	140.3	596.1	7600	128.6	353.5	34.1	26.3
5	1/2	X	27		148.5	668.3	9021	136.1	374.3	36.1	27.8
5	1/2	X	28	1/2	156.8	744.6	10610	143.7	395.1	38.1	29.4
5	1/2	X	30		165.0	825.0	12380	151.3	415.9	40.1	30.9
5	1/2	X	31	1/2	173.3	909.6	14330	158.8	436.7	42.1	32.5
5	1/2	X	33		181.5	998.3	16470	166.4	457.5	44.1	34.0
5	1/2	X	34	1/2	189.8	1091	18820	173.9	478.3	46.1	35.6
5	1/2	X	36		198.0	1188	21380	181.5	499.1	48.1	37.1
5	1/2	X	37	1/2	206.3	1289	24170	189.1	519.9	50.1	38.7
5	1/2	X	39		214.5	1394	27190	196.6	540.7	52.1	40.2
5	1/2	X	40	1/2	222.8	1504	30450	204.2	561.5	54.2	41.8
5	1/2	X	42		231.0	1617	33960	211.8	582.3	56.1	43.3
5	1/2	X	43	1/2	239.3	1735	37730	219.3	603.1	58.2	44.9
5	1/2	X	45		247.5	1856	41770	226.9	623.9	60.2	46.4
5	1/2	X	46	1/2	255.8	1982	46080	234.4	644.7	62.2	48.0
5	1/2	X	48		264.0	2112	50690	242.0	665.5	64.2	49.5
6	3/4	X	3		20.25	10.13	15.19	22.78	76.89	4.9	3.8
6	3/4	X	4	1/2	30.38	22.78	51.26	34.17	115.3	7.4	5.7
6	3/4	X	6		40.50	40.50	121.5	45.56	153.8	9.8	7.6
6	3/4	X	7	1/2	50.63	63.28	237.3	56.95	192.2	12.3	9.5
6	3/4	X	9		60.75	91.13	410.1	68.34	230.7	14.8	11.4
6	3/4	X	10	1/2	70.88	124.0	651.2	79.73	269.1	17.2	13.3
6	3/4	X	12		81.00	162.0	972.0	91.13	307.5	19.7	15.2
6	3/4	X	13	1/2	91.13	205.0	1384	102.5	346.0	22.1	17.1
6	3/4	X	15		101.3	253.1	1898	113.9	384.4	24.6	19.0
6	3/4	X	16	1/2	111.4	306.3	2527	125.3	422.9	27.1	20.9
6	3/4	X	18		121.5	364.5	3281	136.7	461.3	29.5	22.8
6	3/4	X	19	1/2	131.6	427.8	4171	148.1	499.8	32.0	24.7
6	3/4	X	21		141.8	496.1	5209	159.5	538.2	34.5	26.6
6	3/4	X	22	1/2	151.9	569.5	6407	170.9	576.7	36.9	28.5
6	3/4	X	24		162.0	648.0	7776	182.3	615.1	39.4	30.4
6	3/4	X	25	1/2	172.1	731.5	9327	193.6	653.5	41.8	32.3
6	3/4	X	27		182.3	820.1	11070	205.0	692.0	44.3	34.2

Section Properties of Structural Glued Laminated Timber

American Institute of Timber Construction

Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size					x-x Axis			y-y Axis		DF-L	HF
					A	S _x	I _x	S _y	I _y	Weight per foot	Weight per foot
b	d	Area	Section Modulus	Moment of Inertia	Section Modulus	Moment of Inertia	(based on		35 lb/ft ³)	27 lb/ft ³)	
Width	Depth						in. ²	in. ³			in. ⁴
in.	in.										
6	3/4	X	28	1/2	192.4	913.8	13020	216.4	730.4	46.8	36.1
6	3/4	X	30		202.5	1013	15190	227.8	768.9	49.2	38.0
6	3/4	X	31	1/2	212.6	1116	17580	239.2	807.3	51.7	39.9
6	3/4	X	33		222.8	1225	20210	250.6	845.8	54.2	41.8
6	3/4	X	34	1/2	232.9	1339	23100	262.0	884.2	56.6	43.7
6	3/4	X	36		243.0	1458	26240	273.4	922.6	59.1	45.6
6	3/4	X	37	1/2	253.1	1582	29660	284.8	961.1	61.5	47.5
6	3/4	X	39		263.3	1711	33370	296.2	999.5	64.0	49.4
6	3/4	X	40	1/2	273.4	1845	37370	307.5	1038	66.5	51.3
6	3/4	X	42		283.5	1985	41670	318.9	1076	68.9	53.2
6	3/4	X	43	1/2	293.6	2129	46300	330.3	1115	71.4	55.1
6	3/4	X	45		303.8	2278	51260	341.7	1153	73.8	57.0
6	3/4	X	46	1/2	313.9	2433	56560	353.1	1192	76.3	58.9
6	3/4	X	48		324.0	2592	62210	364.5	1230	78.8	60.8
6	3/4	X	49	1/2	334.1	2757	68220	375.9	1269	81.2	62.6
6	3/4	X	51		344.3	2926	74620	387.3	1307	83.7	64.6
6	3/4	X	52	1/2	354.4	3101	81400	398.7	1346	86.1	66.5
6	3/4	X	54		364.5	3281	88570	410.1	1384	88.6	68.3
6	3/4	X	55	1/2	374.6	3465	96160	421.5	1422	91.0	70.2
6	3/4	X	57		384.8	3655	104200	432.8	1461	93.5	72.2
6	3/4	X	58	1/2	394.9	3850	112600	444.2	1499	96.0	74.0
6	3/4	X	60		405.0	4050	121500	455.6	1538	98.4	75.9
8	3/4	X	3		26.25	13.13	19.69	38.28	167.5	6.4	4.9
8	3/4	X	4	1/2	39.38	29.53	66.45	57.42	251.2	9.6	7.4
8	3/4	X	6		52.50	52.50	157.5	76.56	335.0	12.8	9.8
8	3/4	X	7	1/2	65.63	82.03	307.6	95.70	418.7	16.0	12.3
8	3/4	X	9		78.75	118.1	531.6	114.8	502.4	19.1	14.8
8	3/4	X	10	1/2	91.88	160.8	844.1	134.0	586.2	22.3	17.2
8	3/4	X	12		105.0	210.0	1260	153.1	669.9	25.5	19.7
8	3/4	X	13	1/2	118.1	265.8	1794	172.3	753.7	28.7	22.1
8	3/4	X	15		131.3	328.1	2461	191.4	837.4	31.9	24.6
8	3/4	X	16	1/2	144.4	397.0	3276	210.5	921.1	35.1	27.1
8	3/4	X	18		157.5	472.5	4253	229.7	1005	38.3	29.5
8	3/4	X	19	1/2	170.6	554.5	5407	248.8	1089	41.5	32.0
8	3/4	X	21		183.8	643.1	6753	268.0	1172	44.7	34.5
8	3/4	X	22	1/2	196.9	738.3	8306	287.1	1256	47.9	36.9
8	3/4	X	24		210.0	840.0	10080	306.3	1340	51.0	39.4
8	3/4	X	25	1/2	223.1	948.3	12090	325.4	1424	54.2	41.8
8	3/4	X	27		236.3	1063	14350	344.5	1507	57.4	44.3
8	3/4	X	28	1/2	249.4	1185	16880	363.7	1591	60.6	46.8
8	3/4	X	30		262.5	1313	19690	382.8	1675	63.8	49.2
8	3/4	X	31	1/2	275.6	1447	22790	402.0	1759	67.0	51.7
8	3/4	X	33		288.8	1588	26200	421.1	1842	70.2	54.2
8	3/4	X	34	1/2	301.9	1736	29940	440.2	1926	73.4	56.6
8	3/4	X	36		315.0	1890	34020	459.4	2010	76.6	59.1
8	3/4	X	37	1/2	328.1	2051	38450	478.5	2094	79.7	61.5
8	3/4	X	39		341.3	2218	43250	497.7	2177	83.0	64.0

Section Properties of Structural Glued Laminated Timber
American Institute of Timber Construction
Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size				x-x Axis			y-y Axis		DF-L	HF	
				A	S _x	I _x	S _y	I _y	Weight per foot	Weight per foot	
b	d	Area	Section Modulus	Moment of Inertia	Section Modulus	Moment of Inertia	(based on 35 lb/ft ³)	(based on 27 lb/ft ³)			
Width	Depth								in. ²	in. ³	in. ⁴
in.	in.										
8	3/4	X	40	1/2	354.4	2392	48440	516.8	2261	86.1	66.5
8	3/4	X	42		367.5	2573	54020	535.9	2345	89.3	68.9
8	3/4	X	43	1/2	380.6	2760	60020	555.1	2428	92.5	71.4
8	3/4	X	45		393.8	2953	66450	574.2	2512	95.7	73.8
8	3/4	X	46	1/2	406.9	3153	73310	593.4	2596	98.9	76.3
8	3/4	X	48		420.0	3360	80640	612.5	2680	102.1	78.8
8	3/4	X	49	1/2	433.1	3573	88440	631.6	2763	105.3	81.2
8	3/4	X	51		446.3	3793	96720	650.8	2847	108.5	83.7
8	3/4	X	52	1/2	459.4	4020	105500	669.9	2931	111.7	86.1
8	3/4	X	54		472.5	4253	114800	689.1	3015	114.8	88.6
8	3/4	X	55	1/2	485.6	4492	124700	708.2	3098	118.0	91.1
8	3/4	X	57		498.8	4738	135000	727.3	3182	121.2	93.5
8	3/4	X	58	1/2	511.9	4991	146000	746.5	3266	124.4	96.0
8	3/4	X	60		525.0	5250	157500	765.6	3350	127.6	98.4
8	3/4	X	61	1/2	538.1	5516	169600	784.8	3433	130.8	100.9
8	3/4	X	63		551.3	5788	182300	803.9	3517	134.0	103.4
8	3/4	X	64	1/2	564.4	6067	195700	823.0	3601	137.2	105.8
8	3/4	X	66		577.5	6353	209600	842.2	3685	140.4	108.3
8	3/4	X	67	1/2	590.6	6645	224300	861.3	3768	143.5	110.7
8	3/4	X	69		603.8	6943	239500	880.5	3852	146.8	113.2
8	3/4	X	70	1/2	616.9	7248	255500	899.6	3936	149.9	115.7
8	3/4	X	72		630.0	7560	272200	918.8	4020	153.1	118.1
8	3/4	X	73	1/2	643.1	7878	289500	937.9	4103	156.3	120.6
8	3/4	X	75		656.3	8203	307600	957.0	4187	159.5	123.1
10	3/4	X	3		32.25	16.13	24.19	57.78	310.6	7.8	6.0
10	3/4	X	4	1/2	48.38	36.28	81.63	86.67	465.9	11.8	9.1
10	3/4	X	6		64.50	64.50	193.5	115.6	621.1	15.7	12.1
10	3/4	X	7	1/2	80.63	100.8	377.9	144.5	776.4	19.6	15.1
10	3/4	X	9		96.75	145.1	653.1	173.3	931.7	23.5	18.1
10	3/4	X	10	1/2	112.9	197.5	1037	202.2	1087	27.4	21.2
10	3/4	X	12		129.0	258.0	1548	231.1	1242	31.4	24.2
10	3/4	X	13	1/2	145.1	326.5	2204	260.0	1398	35.3	27.2
10	3/4	X	15		161.3	403.1	3023	288.9	1553	39.2	30.2
10	3/4	X	16	1/2	177.4	487.8	4024	317.8	1708	43.1	33.3
10	3/4	X	18		193.5	580.5	5225	346.7	1863	47.0	36.3
10	3/4	X	19	1/2	209.6	681.3	6642	375.6	2019	50.9	39.3
10	3/4	X	21		225.8	790.1	8296	404.5	2174	54.9	42.3
10	3/4	X	22	1/2	241.9	907.0	10200	433.4	2329	58.8	45.4
10	3/4	X	24		258.0	1032	12380	462.3	2485	62.7	48.4
10	3/4	X	25	1/2	274.1	1165	14850	491.1	2640	66.6	51.4
10	3/4	X	27		290.3	1306	17630	520.0	2795	70.6	54.4
10	3/4	X	28	1/2	306.4	1455	20740	548.9	2950	74.5	57.5
10	3/4	X	30		322.5	1613	24190	577.8	3106	78.4	60.5
10	3/4	X	31	1/2	338.6	1778	28000	606.7	3261	82.3	63.5
10	3/4	X	33		354.8	1951	32190	635.6	3416	86.2	66.5
10	3/4	X	34	1/2	370.9	2133	36790	664.5	3572	90.1	69.5
10	3/4	X	36		387.0	2322	41800	693.4	3727	94.1	72.6

Section Properties of Structural Glued Laminated Timber
American Institute of Timber Construction
Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size				x-x Axis			y-y Axis		DF-L	HF	
				A	S _x	I _x	S _y	I _y	Weight per foot	Weight per foot	
b	d	Area	Section Modulus	Moment of Inertia	Section Modulus	Moment of Inertia	(based on 35 lb/ft ³)	(based on 27 lb/ft ³)			
Width	Depth								in. ²	in. ³	in. ⁴
10	3/4	X	37	1/2	403.1	2520	47240	722.3	3882	98.0	75.6
10	3/4	X	39		419.3	2725	53140	751.2	4037	101.9	78.6
10	3/4	X	40	1/2	435.4	2939	59510	780.0	4193	105.8	81.6
10	3/4	X	42		451.5	3161	66370	808.9	4348	109.7	84.7
10	3/4	X	43	1/2	467.6	3390	73740	837.8	4503	113.7	87.7
10	3/4	X	45		483.8	3628	81630	866.7	4659	117.6	90.7
10	3/4	X	46	1/2	499.9	3874	90070	895.6	4814	121.5	93.7
10	3/4	X	48		516.0	4128	99070	924.5	4969	125.4	96.8
10	3/4	X	49	1/2	532.1	4390	108700	953.4	5124	129.3	99.8
10	3/4	X	51		548.3	4660	118800	982.3	5280	133.3	102.8
10	3/4	X	52	1/2	564.4	4938	129600	1011	5435	137.2	105.8
10	3/4	X	54		580.5	5225	141100	1040	5590	141.1	108.8
10	3/4	X	55	1/2	596.6	5519	153100	1069	5746	145.0	111.9
10	3/4	X	57		612.8	5821	165900	1098	5901	148.9	114.9
10	3/4	X	58	1/2	628.9	6132	179300	1127	6056	152.9	117.9
10	3/4	X	60		645.0	6450	193500	1156	6211	156.8	120.9
10	3/4	X	61	1/2	661.1	6777	208400	1185	6367	160.7	124.0
10	3/4	X	63		677.3	7111	224000	1213	6522	164.6	127.0
10	3/4	X	64	1/2	693.4	7454	240400	1242	6677	168.5	130.0
10	3/4	X	66		709.5	7805	257500	1271	6833	172.4	133.0
10	3/4	X	67	1/2	725.6	8163	275500	1300	6988	176.4	136.1
10	3/4	X	69		741.8	8530	294300	1329	7143	180.3	139.1
10	3/4	X	70	1/2	757.9	8905	313900	1358	7298	184.2	142.1
10	3/4	X	72		774.0	9288	334400	1387	7454	188.1	145.1
10	3/4	X	73	1/2	790.1	9679	355700	1416	7609	192.0	148.1
10	3/4	X	75		806.3	10080	377900	1445	7764	196.0	151.2
10	3/4	X	76	1/2	822.4	10490	401100	1473	7920	199.9	154.2
10	3/4	X	78		838.5	10900	425100	1502	8075	203.8	157.2
10	3/4	X	79	1/2	854.6	11320	450100	1531	8230	207.7	160.2
10	3/4	X	81		870.8	11760	476100	1560	8386	211.7	163.3
10	3/4	X	82	1/2	886.9	12190	503000	1589	8541	215.6	166.3
10	3/4	X	84		903.0	12640	531000	1618	8696	219.5	169.3
10	3/4	X	85	1/2	919.1	13100	559900	1647	8851	223.4	172.3
10	3/4	X	87		935.3	13560	589900	1676	9007	227.3	175.4
10	3/4	X	88	1/2	951.4	14030	621000	1705	9162	231.2	178.4
10	3/4	X	90		967.5	14510	653100	1733	9317	235.2	181.4
12	1/4	X	3		36.75	18.38	27.56	75.03	459.6	8.9	6.9
12	1/4	X	4	1/2	55.13	41.34	93.02	112.5	689.3	13.4	10.3
12	1/4	X	6		73.50	73.50	220.5	150.1	919.1	17.9	13.8
12	1/4	X	7	1/2	91.88	114.8	430.7	187.6	1149	22.3	17.2
12	1/4	X	9		110.3	165.4	744.2	225.1	1379	26.8	20.7
12	1/4	X	10	1/2	128.6	225.1	1182	262.6	1608	31.3	24.1
12	1/4	X	12		147.0	294.0	1764	300.1	1838	35.7	27.6
12	1/4	X	13	1/2	165.4	372.1	2512	337.6	2068	40.2	31.0
12	1/4	X	15		183.8	459.4	3445	375.2	2298	44.7	34.5
12	1/4	X	16	1/2	202.1	555.8	4586	412.7	2528	49.1	37.9
12	1/4	X	18		220.5	661.5	5954	450.2	2757	53.6	41.3

Section Properties of Structural Glued Laminated Timber

American Institute of Timber Construction

Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size				x-x Axis			y-y Axis		DF-L	HF	
				A	S _x	I _x	S _y	I _y	Weight per foot	Weight per foot	
b	d	Area	Section Modulus	Moment of Inertia	Section Modulus	Moment of Inertia	(based on 35 lb/ft ³)	(based on 27 lb/ft ³)			
Width	Depth	in. ²	in. ³	in. ⁴	in. ³	in. ⁴	lb/ft	lb/ft			
in.	in.										
12	1/4	X	19	1/2	238.9	776.3	7569	487.7	2987	58.1	44.8
12	1/4	X	21		257.3	900.4	9454	525.2	3217	62.5	48.2
12	1/4	X	22	1/2	275.6	1034	11630	562.7	3447	67.0	51.7
12	1/4	X	24		294.0	1176	14110	600.3	3677	71.5	55.1
12	1/4	X	25	1/2	312.4	1328	16930	637.8	3906	75.9	58.6
12	1/4	X	27		330.8	1488	20090	675.3	4136	80.4	62.0
12	1/4	X	28	1/2	349.1	1658	23630	712.8	4366	84.9	65.5
12	1/4	X	30		367.5	1838	27560	750.3	4596	89.3	68.9
12	1/4	X	31	1/2	385.9	2026	31910	787.8	4825	93.8	72.4
12	1/4	X	33		404.3	2223	36690	825.3	5055	98.3	75.8
12	1/4	X	34	1/2	422.6	2430	41920	862.9	5285	102.7	79.2
12	1/4	X	36		441.0	2646	47630	900.4	5515	107.2	82.7
12	1/4	X	37	1/2	459.4	2871	53830	937.9	5745	111.7	86.1
12	1/4	X	39		477.8	3105	60550	975.4	5974	116.1	89.6
12	1/4	X	40	1/2	496.1	3349	67810	1013	6204	120.6	93.0
12	1/4	X	42		514.5	3602	75630	1050	6434	125.1	96.5
12	1/4	X	43	1/2	532.9	3863	84030	1088	6664	129.5	99.9
12	1/4	X	45		551.3	4134	93020	1125	6893	134.0	103.4
12	1/4	X	46	1/2	569.6	4415	102600	1163	7123	138.4	106.8
12	1/4	X	48		588.0	4704	112900	1201	7353	142.9	110.3
12	1/4	X	49	1/2	606.4	5003	123800	1238	7583	147.4	113.7
12	1/4	X	51		624.8	5310	135400	1276	7813	151.9	117.2
12	1/4	X	52	1/2	643.1	5627	147700	1313	8042	156.3	120.6
12	1/4	X	54		661.5	5954	160700	1351	8272	160.8	124.0
12	1/4	X	55	1/2	679.9	6289	174500	1388	8502	165.3	127.5
12	1/4	X	57		698.3	6633	189100	1426	8732	169.7	130.9
12	1/4	X	58	1/2	716.6	6987	204400	1463	8962	174.2	134.4
12	1/4	X	60		735.0	7350	220500	1501	9191	178.6	137.8
12	1/4	X	61	1/2	753.4	7722	237500	1538	9421	183.1	141.3
12	1/4	X	63		771.8	8103	255300	1576	9651	187.6	144.7
12	1/4	X	64	1/2	790.1	8494	273900	1613	9881	192.0	148.1
12	1/4	X	66		808.5	8894	293500	1651	10110	196.5	151.6
12	1/4	X	67	1/2	826.9	9302	314000	1688	10340	201.0	155.0
12	1/4	X	69		845.3	9720	335400	1726	10570	205.5	158.5
12	1/4	X	70	1/2	863.6	10150	357700	1763	10800	209.9	161.9
12	1/4	X	72		882.0	10580	381000	1801	11030	214.4	165.4
12	1/4	X	73	1/2	900.4	11030	405300	1838	11260	218.8	168.8
12	1/4	X	75		918.8	11480	430700	1876	11490	223.3	172.3
12	1/4	X	76	1/2	937.1	11950	457000	1913	11720	227.8	175.7
12	1/4	X	78		955.5	12420	484400	1951	11950	232.2	179.2
12	1/4	X	79	1/2	973.9	12900	512900	1988	12180	236.7	182.6
12	1/4	X	81		992.3	13400	542500	2026	12410	241.2	186.1
12	1/4	X	82	1/2	1011	13900	573200	2063	12640	245.7	189.6
12	1/4	X	84		1029	14410	605100	2101	12870	250.1	192.9
12	1/4	X	85	1/2	1047	14930	638000	2138	13100	254.5	196.3
12	1/4	X	87		1066	15450	672200	2176	13330	259.1	199.9
12	1/4	X	88	1/2	1084	15990	707600	2213	13560	263.5	203.3

Section Properties of Structural Glued Laminated Timber
American Institute of Timber Construction
Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size				x-x Axis			y-y Axis		DF-L	HF
				A	S _x	I _x	S _y	I _y	Weight per foot (based on 35 lb/ft ³)	Weight per foot (based on 27 lb/ft ³)
b	d	Area in. ²	Section Modulus in. ³	Moment of Inertia in. ⁴	Section Modulus in. ³	Moment of Inertia in. ⁴	lb/ft	lb/ft		
Width in.	Depth in.									
12	1/4	X	90	1103	16540	744200	2251	13790	268.1	206.8
12	1/4	X	91 1/2	1121	17090	782000	2288	14020	272.5	210.2
12	1/4	X	93	1139	17660	821100	2326	14250	276.8	213.6
12	1/4	X	94 1/2	1158	18230	861500	2363	14480	281.5	217.1
12	1/4	X	96	1176	18820	903200	2401	14710	285.8	220.5
12	1/4	X	97 1/2	1194	19410	946200	2439	14940	290.2	223.9
12	1/4	X	99	1213	20010	990500	2476	15170	294.8	227.4
12	1/4	X	100 1/2	1231	20620	1036000	2514	15400	299.2	230.8
12	1/4	X	102	1250	21240	1083000	2551	15630	303.8	234.4
12	1/4	X	103 1/2	1268	21870	1132000	2589	15860	308.2	237.8
12	1/4	X	105	1286	22510	1182000	2626	16080	312.6	241.1
12	1/4	X	106 1/2	1305	23160	1233000	2664	16310	317.2	244.7
12	1/4	X	108	1323	23810	1286000	2701	16540	321.6	248.1
12	1/4	X	109 1/2	1341	24480	1340000	2739	16770	325.9	251.4
12	1/4	X	111	1360	25160	1396000	2776	17000	330.6	255.0
12	1/4	X	112 1/2	1378	25840	1453000	2814	17230	334.9	258.4
14	1/4	X	3	42.75	21.38	32.06	101.5	723.4	10.4	8.0
14	1/4	X	4 1/2	64.13	48.09	108.2	152.3	1085	15.6	12.0
14	1/4	X	6	85.50	85.50	256.5	203.1	1447	20.8	16.0
14	1/4	X	7 1/2	106.9	133.6	501.0	253.8	1809	26.0	20.0
14	1/4	X	9	128.3	192.4	865.7	304.6	2170	31.2	24.1
14	1/4	X	10 1/2	149.6	261.8	1375	355.4	2532	36.4	28.1
14	1/4	X	12	171.0	342.0	2052	406.1	2894	41.6	32.1
14	1/4	X	13 1/2	192.4	432.8	2922	456.9	3255	46.8	36.1
14	1/4	X	15	213.8	534.4	4008	507.7	3617	52.0	40.1
14	1/4	X	16 1/2	235.1	646.6	5334	558.4	3979	57.1	44.1
14	1/4	X	18	256.5	769.5	6926	609.2	4340	62.3	48.1
14	1/4	X	19 1/2	277.9	903.1	8805	660.0	4702	67.5	52.1
14	1/4	X	21	299.3	1047	11000	710.7	5064	72.7	56.1
14	1/4	X	22 1/2	320.6	1202	13530	761.5	5426	77.9	60.1
14	1/4	X	24	342.0	1368	16420	812.3	5787	83.1	64.1
14	1/4	X	25 1/2	363.4	1544	19690	863.0	6149	88.3	68.1
14	1/4	X	27	384.8	1731	23370	913.8	6511	93.5	72.2
14	1/4	X	28 1/2	406.1	1929	27490	964.5	6872	98.7	76.1
14	1/4	X	30	427.5	2138	32060	1015	7234	103.9	80.2
14	1/4	X	31 1/2	448.9	2357	37120	1066	7596	109.1	84.2
14	1/4	X	33	470.3	2586	42680	1117	7958	114.3	88.2
14	1/4	X	34 1/2	491.6	2827	48760	1168	8319	119.5	92.2
14	1/4	X	36	513.0	3078	55400	1218	8681	124.7	96.2
14	1/4	X	37 1/2	534.4	3340	62620	1269	9043	129.9	100.2
14	1/4	X	39	555.8	3612	70440	1320	9404	135.1	104.2
14	1/4	X	40 1/2	577.1	3896	78890	1371	9766	140.3	108.2
14	1/4	X	42	598.5	4190	87980	1421	10130	145.5	112.2
14	1/4	X	43 1/2	619.9	4494	97750	1472	10490	150.7	116.2
14	1/4	X	45	641.3	4809	108200	1523	10850	155.9	120.2
14	1/4	X	46 1/2	662.6	5135	119400	1574	11210	161.0	124.2
14	1/4	X	48	684.0	5472	131300	1625	11570	166.3	128.3

Section Properties of Structural Glued Laminated Timber

American Institute of Timber Construction

Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size					x-x Axis			y-y Axis		DF-L	HF
					A	S _x	I _x	S _y	I _y	Weight per foot	Weight per foot
b	d	Area	Section Modulus	Moment of Inertia	Section Modulus	Moment of Inertia	(based on		35 lb/ft ³)	27 lb/ft ³)	
Width	Depth						in. ²	in. ³			in. ⁴
in.	in.										
14	1/4	X 49	1/2	705.4	5819	144000	1675	11940	171.5	132.3	
14	1/4	X 51		726.8	6177	157500	1726	12300	176.7	136.3	
14	1/4	X 52	1/2	748.1	6546	171800	1777	12660	181.8	140.3	
14	1/4	X 54		769.5	6926	187000	1828	13020	187.0	144.3	
14	1/4	X 55	1/2	790.9	7316	203000	1878	13380	192.2	148.3	
14	1/4	X 57		812.3	7716	219900	1929	13740	197.4	152.3	
14	1/4	X 58	1/2	833.6	8128	237700	1980	14110	202.6	156.3	
14	1/4	X 60		855.0	8550	256500	2031	14470	207.8	160.3	
14	1/4	X 61	1/2	876.4	8983	276200	2081	14830	213.0	164.3	
14	1/4	X 63		897.8	9426	296900	2132	15190	218.2	168.3	
14	1/4	X 64	1/2	919.1	9881	318600	2183	15550	223.4	172.3	
14	1/4	X 66		940.5	10350	341400	2234	15920	228.6	176.3	
14	1/4	X 67	1/2	961.9	10820	365200	2284	16280	233.8	180.4	
14	1/4	X 69		983.3	11310	390100	2335	16640	239.0	184.4	
14	1/4	X 70	1/2	1005	11800	416100	2386	17000	244.3	188.4	
14	1/4	X 72		1026	12310	443200	2437	17360	249.4	192.4	
14	1/4	X 73	1/2	1047	12830	471500	2488	17720	254.5	196.3	
14	1/4	X 75		1069	13360	501000	2538	18090	259.8	200.4	
14	1/4	X 76	1/2	1090	13900	531600	2589	18450	264.9	204.4	
14	1/4	X 78		1112	14450	563500	2640	18810	270.3	208.5	
14	1/4	X 79	1/2	1133	15010	596700	2691	19170	275.4	212.4	
14	1/4	X 81		1154	15580	631100	2741	19530	280.5	216.4	
14	1/4	X 82	1/2	1176	16160	666800	2792	19890	285.8	220.5	
14	1/4	X 84		1197	16760	703800	2843	20260	290.9	224.4	
14	1/4	X 85	1/2	1218	17360	742200	2894	20620	296.0	228.4	
14	1/4	X 87		1240	17980	782000	2944	20980	301.4	232.5	
14	1/4	X 88	1/2	1261	18600	823100	2995	21340	306.5	236.4	
14	1/4	X 90		1283	19240	865700	3046	21700	311.8	240.6	
14	1/4	X 91	1/2	1304	19880	909700	3097	22060	316.9	244.5	
14	1/4	X 93		1325	20540	955200	3147	22430	322.0	248.4	
14	1/4	X 94	1/2	1347	21210	1002000	3198	22790	327.4	252.6	
14	1/4	X 96		1368	21890	1051000	3249	23150	332.5	256.5	
14	1/4	X 97	1/2	1389	22580	1101000	3300	23510	337.6	260.4	
14	1/4	X 99		1411	23280	1152000	3351	23870	343.0	264.6	
14	1/4	X 100	1/2	1432	23990	1205000	3401	24230	348.1	268.5	
14	1/4	X 102		1454	24710	1260000	3452	24600	353.4	272.6	
14	1/4	X 103	1/2	1475	25440	1317000	3503	24960	358.5	276.6	
14	1/4	X 105		1496	26180	1375000	3554	25320	363.6	280.5	
14	1/4	X 106	1/2	1518	26940	1434000	3604	25680	369.0	284.6	
14	1/4	X 108		1539	27700	1496000	3655	26040	374.1	288.6	
14	1/4	X 109	1/2	1560	28480	1559000	3706	26400	379.2	292.5	
14	1/4	X 111		1582	29260	1624000	3757	26770	384.5	296.6	
14	1/4	X 112	1/2	1603	30060	1691000	3807	27130	389.6	300.6	
14	1/4	X 114		1625	30870	1759000	3858	27490	395.0	304.7	
14	1/4	X 115	1/2	1646	31680	1830000	3909	27850	400.1	308.6	
14	1/4	X 117		1667	32510	1902000	3960	28210	405.2	312.6	
14	1/4	X 118	1/2	1689	33350	1976000	4010	28570	410.5	316.7	

Section Properties of Structural Glued Laminated Timber
American Institute of Timber Construction
Western Species (Based on 1-1/2 in. Thick Laminations)

Beam Size				x-x Axis			y-y Axis		DF-L	HF
				A	S_x	I_x	S_y	I_y	Weight per foot	Weight per foot
b	d	Area	Section Modulus	Moment of Inertia	Section Modulus	Moment of Inertia	(based on 35 lb/ft ³)	(based on 27 lb/ft ³)		
Width	Depth								in. ²	in. ³
14	1/4	X 120	1710	34200	2052000	4061	28940	415.6	320.6	
14	1/4	X 121 1/2	1731	35060	2130000	4112	29300	420.7	324.6	
14	1/4	X 123	1753	35930	2210000	4163	29660	426.1	328.7	
14	1/4	X 124 1/2	1774	36810	2292000	4214	30020	431.2	332.6	
14	1/4	X 126	1796	37710	2375000	4264	30380	436.5	336.8	
14	1/4	X 127 1/2	1817	38610	2461000	4315	30740	441.6	340.7	
14	1/4	X 129	1838	39520	2549000	4366	31110	446.7	344.6	
14	1/4	X 130 1/2	1860	40450	2639000	4417	31470	452.1	348.8	

AITC MAKES NO REPRESENTATION OR WARRANTY, EXPRESSED OR IMPLIED, THAT THE INFORMATION CONTAINED HEREIN IS SUITABLE FOR ANY GENERAL OR SPECIFIC USE OR IS FREE FROM INFRINGEMENT OF ANY PATENT OR COPYRIGHT. ANY USER OF THIS INFORMATION ASSUMES ALL RISK AND LIABILITY ARISING FROM SUCH USE